



CERTIFICATE OF TESTING

For the Account Of: Mokum Textiles
Mezzanine Level, Suite 14, Level 1
69 O'Riordan Street
Alexandria, NSW 2015
Australia
Contact: Dorit Herrmann

Client's Identification: Joss

TEST PERFORMED NFPA 260 Standard Methods of Tests and Classification System for Cigarette Ignition Resistance of Components of Upholstered Furniture – 2013; Fabric Cover Test and UFAC Fabric Classification Test Method – 1990; Standard Test Methods for Cigarette Ignition Resistance of Components of Upholstered Furniture ASTM E1353-08ae1 – Cover Fabric Test

TEST RESULTS

Specimen	Char Length (in)
1	Obvious Ignition of Substrate
2	Obvious Ignition of Substrate
3	Obvious Ignition of Substrate

NOTES
Test Conditions: 70 ±2°F, 65 ±2% Relative Humidity

- ACCEPTANCE CRITERIA**
1. If the test specimen has no ignition, or if no individual specimen yields a vertical char of 45 mm (1.75 in; ASTM states 1.8 in.) or less, the fabric is classified a Class I cover fabric.
 2. If the vertical char of the test specimen greater than 45 mm (1.75 in.; ASTM states 1.8 in), the fabric is classified a Class II cover fabric.
 3. If an obvious ignition of the polyurethane substrate occurs on the test assembly, the fabric is classified a Class II cover fabric.

CONCLUSION Based on the above Results and Acceptance Criteria, the item tested is:
 Class I
 Class II

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

C. Venturini

Authorized Signature-MB