

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd – trading as AWTA Product Testing
A.B.N. 43 006 014 106
1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O. Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client: James Dunlop Textiles
Suite 14, Level 1
69 O'Riordan Street
Alexandria NSW 2015

Test Number : 14-000989
Issue Date : 24/10/2014
Print Date : 24/10/2014
Order Number : PO-Kuma

Sample Description Clients Ref: "Kuma"
Woven back laminated dobby fabric
Colour: 110 Java (Blue/Brown)
End Use: Upholstery
Nominal Composition: 100% Polyester
Nominal Mass per Unit Area/Density: 286g/m2

AS/NZS 1530.3-1999

**Methods for Fire Tests on Building Materials, Components and Structures Part 3:
Simultaneous Determination of Ignitability, Flame Propagation, Heat Release and Smoke
Release**

Face tested: Face
Date tested: 24/10/2014

	Standard Error	Mean	
Ignition time	0.15	8.09	min
Flame propagation time	Nil	Nil	sec
Heat release integral	2.4	85.6	kJ/m ²
Smoke release, log d	0.0116	-0.6992	
Optical density, d		0.2002	/ metre

Number of specimens ignited: 6

Number of specimens tested: 6

Regulatory Indices:

Ignitability Index: 12 Range 0-20

Spread of Flame Index: 0 Range 0-10

Heat Evolved Index: 3 Range 0-10

Smoke Developed Index: 5 Range 0-10

5787

1140

Page 1 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



This Laboratory is accredited by the National Association of Testing Authorities, Australia, for:
- Chemical Testing of Textiles & Related Products : Accreditation No. 983
- Mechanical Testing of Textiles & Related Products : Accreditation No. 985
- Heat & Temperature Measurement : Accreditation No. 1356

This document is issued in accordance with NATA's accreditation requirements. Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the Managing Director of AWTA Ltd.



APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc. (Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd – trading as AWTA Product Testing
A.B.N. 43 006 014 106
1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O. Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client : James Dunlop Textiles
Suite 14, Level 1
69 O'Riordan Street
Alexandria NSW 2015

Test Number : 14-000989
Issue Date : 24/10/2014
Print Date : 24/10/2014
Order Number : PO-Kuma

These results only apply to the specimen mounted, as described in this report. The result of this fire test may be used to directly assess fire hazard, but it should be recognised that a single test method will not provide a full assessment of fire hazard under all fire conditions.

The reaction of thin unsupported flexible materials to flame impingement can be assessed in accordance with AS 1530.2. Where materials of thickness less than 2mm that are sufficiently flexible to be bent by hand around a mandrel of 2mm diameter or less are subjected to the test described herein, they should also be subjected to the test in AS 1530.2.

Each test specimen had an unattached backing of 4.5mm thick fibre reinforced cement board.

Each test specimen was restrained on the exposed face by a layer of galvanised welded square mesh made from wire of nominal diameter 0.8mm and nominal spacing 12mm in both directions and securely fixed to a backing board at four points each 100mm from the centre of the sample and the assembly clamped in four places.

To allow free movement of sample during testing all corners were folded away from the clamps.

5787

1140

Page 2 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



This Laboratory is accredited by the National Association of Testing Authorities, Australia, for:

- Chemical Testing of Textiles & Related Products	: Accreditation No. 983
- Mechanical Testing of Textiles & Related Products	: Accreditation No. 985
- Heat & Temperature Measurement	: Accreditation No. 1356

This document is issued in accordance with NATA's accreditation requirements. Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the Managing Director of AWTA Ltd.



0204/11/06

APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR