



Textile Testing

553 76th Street · Byron Center, MI 49315 Phone: 616.559.6123 Fax: 616.559.6119



TESTING CERT. #3193.01

Report Number: 46746
Date: 07-06-2011

For the Account Of: Mokum Textiles
19A Boundary Street
Darlinghurst, NSW 2010
Australia
Contact: Dorit Herrmann

Client's Identification: Esplanade

Test Performed NFPA 260 Standard Methods of Tests and Classification System for Cigarette Ignition Resistance of Components of Upholstered Furniture – 2009: Fabric Cover Test and UFAC Fabric Classification Test Method – 1990

TEST DATA

| Specimen # | Char Length (inches) |
|------------|----------------------|
| 1 | 0.9 |
| 2 | 0.9 |
| 3 | 0.8 |

NOTES

Test Conditions: 70 ±2°F, 65 ±2% Relative Humidity

ACCEPTANCE CRITERIA

1. If the test specimen has no ignition, or if no individual specimen yields a vertical char of 44 mm (1.75 in.) or less, the fabric is classified a UFAC and NFPA Class I cover fabric.
2. If the vertical char of the test specimen greater than 45 mm (1.75 in.), the fabric is classified a UFAC Class II cover fabric.
3. If an obvious ignition of the polyurethane substrate occurs on the test assembly, the fabric is classified a UFAC Class II cover fabric.

CONCLUSION

Based on the above Results and Acceptance Criteria, the item tested is:
 Class I
 Class II

CERTIFICATION: I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature *Jennifer Hund*