

CERTIFICATE OF TESTING

For the Account Of: James Dunlop Textiles Ltd
PO Box 1636
Christchurch 8140
New Zealand
Contact: Angela Storey

Client's Identification: Nirvana 12271

TEST PERFORMED Abrasion Resistance of Textile Fabrics (Oscillatory Cylinder Method) ASTM D4157-13

TEST RESULTS

Number of Double Rubs	Warp (Length) Specimens	Fill (Width) Specimens
100,000	No breakage / wear	Breakage occurred

INTERPRETATION USED

- Option 1 The end point is reached on a woven fabric when two or more yarns have broken or on a knitted fabric, when a hole appears.
 Option 2 The end point is reached when there is a change in shade or appearance that is sufficient to cause a customer to complain.

NOTES

Abradant Used: ACT Standard #10 Cotton Duck Wire Screen
Samples Backed with Masking Tape: Yes No
Tension: 4 pounds
Compression: 3 pounds

ACCEPTANCE CRITERIA

A.C.T. Standard	Acceptance Criteria
General Contract Upholstery	No appreciable breakage or wear after 15,000 double rubs
Heavy Duty Upholstery	No appreciable breakage or wear after 30,000 double rubs

CONCLUSION

Based on the above Results and the A.C.T. Standard, the item tested:
 Unrated
 General Contract Upholstery
 Heavy Duty Upholstery

CERTIFICATION I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.


Authorized Signature