

**CERTIFICATE OF TESTING**

For the Account Of: Mokum Textiles  
Suite 18, Level 1  
69 O’Riordan Street  
Alexandria, NSW 2015  
Australia  
Contact: Annie Moir

Client’s Identification: Medina 12415

**TEST PERFORMED** Abrasion Resistance of Textile Fabrics (Oscillatory Cylinder Method) ASTM D3597-02(2013) / ASTM D4157-13

**TEST RESULTS**

Number of Double Rubs	Warp (Length) Specimens	Fill (Width) Specimens
39,000	No breakage/wear	Breakage in 1 <sup>st</sup> specimen
48,000	No breakage/wear	Breakage in 2 <sup>nd</sup> specimen

**INTERPRETATION USED:**

- Option 1 The end point is reached on a woven fabric when two or more yarns have broken or on a knitted fabric, when a hole appears.
- Option 2 The end point is reached when there is a change in shade or appearance that is sufficient to cause a customer to complain.

**NOTES**

**Abradant Used:**  ACT Standard #10 Cotton Duck  Wire Screen  
**Samples Backed with Masking Tape:**  Yes  No  
**Tension:** 4 pounds  
**Compression:** 3 pounds


**ACCEPTANCE CRITERIA**

Residential Standard	Acceptance Criteria
Light Duty	No appreciable breakage or wear after 3,000 double rubs, but shows wear after 9,000 double rubs
Medium Duty	No appreciable breakage or wear after 9,000 double rubs, but shows wear after 15,000 double rubs
Heavy Duty	No appreciable breakage or wear after 15,000 double rubs

**CONCLUSION**

Based on the above Results and the Residential Standard, the item tested:  
 Unrated  
 Light Duty  
 Medium Duty  
 Heavy Duty

**CERTIFICATION** I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

  
Authorized Signature CR