



TESTING CERT. #3193.01

Report Number: 18-005512  
Revision Number:1  
Date Order Received: 09/07/2018

For the Account of: James Dunlop Textiles  
PO Box 1636  
Christchurch 8140  
New Zealand

Client's Identification: Chelsea

### CERTIFICATE OF TESTING

**TEST PERFORMED:** NFPA 260 Standard Methods of Tests and Classification System for Cigarette Ignition Resistance of Components of Upholstered Furniture – 2013; Fabric Cover Test and UFAC Fabric Classification Test Method – 1990; Standard Test Methods for Cigarette Ignition Resistance of Components of Upholstered Furniture ASTM E 1353-16 – Cover Fabric Test

#### TEST RESULTS

Specimen	Char Length (in)
1	0.4
2	0.4
3	0.5

#### NOTES

**Test Conditions:** 70 ±4°F, 65 ±5% Relative Humidity

Dev-009: Used SRM 1196 Equivalent YES  
Lot # 18140130548

#### ACCEPTANCE CRITERIA

1. If the test specimen has no ignition, or if no individual specimen yields a vertical char of 45 mm (1.75 in; ASTM states 1.8 in.) or less, the fabric is classified a Class I cover fabric.
2. If the vertical char of the test specimen greater than 45 mm (1.75 in.; ASTM states 1.8 in), the fabric is classified a Class II cover fabric.
3. If an obvious ignition of the polyurethane substrate occurs on the test assembly, the fabric is classified a Class II cover fabric.

**CONCLUSION** Based on the above Results and Acceptance Criteria, the item tested is:

- Class I
- Class II

**CERTIFICATION** I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature

Date Order Completed: 09/18/2018