



Textile Testing

553 76th Street · Byron Center, MI 49315 Phone: 616.559.6123 Fax: 616.559.6119



TESTING CERT. #3193.01

Report Number: 50972
Date: 03-05-2012

For the Account Of: Mokum Design Studios
Suite 308; Level 3
19A Boundary Street
Darlinghurst NSW 2010
AUSTRALIA
Contact: Dorit Herrmann

Client's Identification: Tahiti

Test Performed California Technical Bulletin 117, Section E (CPSC 16 CFR 1610 – CS 191-53) Upholstery
Fabrics, March 2000

TEST DATA

Plain Surface

Raised Surface

Specimen	Flame Spread	Flame Spread
	Warp Face (seconds)	Warp Back (seconds)
1	DNI	
2	DNI	
3	DNI	
4		DNI
5		DNI

Specimen	Flame Spread	Flame Spread
	Fill Face (seconds)	Fill Back (seconds)
1	DNI	
2	DNI	
3	DNI	
4		DNI
5		DNI

ABBREVIATIONS USED

- DNI Did not ignite when exposed to test ignition source
- IBE Ignited but extinguished before burning through stop cord
- SF Surface flash only; stop cord not burned & no burning/charring/fusing of the base fabric
- TSF Timed surface flash; stop cord burned, but no burning/charring/fusing of the base fabric

ACCEPTANCE CRITERIA

1. With nap - Minimum flame spread of any individual specimens shall be 7 seconds. (ACT Criteria decreases minimum time to 4 seconds)
2. Without nap - Minimum flame spread of any individual specimens shall be 3.5 seconds.

CONCLUSION Based on the above Results and Acceptance Criteria, the item tested:

- Complies
- Does Not Comply

CERTIFICATION: I certify that the above results were obtained after testing specimen in accordance with the procedures and equipment specified by the standard stated above.

Authorized Signature